

**Model:** TANZANIA WHITE(24C/P) 25X150(A)

**Codes:** 100297209

**Water absorption:** Bla - Porcelanico (E<=0.1%)



## DIMENSIONAL FEATURES UNE-EN ISO 10545-2

Thickness	11 MM	+/-5%*
Width	250 MM	
Length	1500 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

\*ISO-13006:2018 UNE-EN 14411:2016

## MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11

Breaking strength	3507 N	>1300N*
Modulus of rupture	54 N/MM2	>=35N/mm2*
Abrasion resistance	PEI 4 / 1500v	
Crazing resistance	Resists 3 cycles	

\*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

\*ISO-13006:2018 UNE-EN 14411:2016

## SCOPE OF USE

Technical code-1	Use on medium traffic floors
------------------	------------------------------

## ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028

Dynamic coefficient of friction	>0.42
Slip resistance (pendulum-wet)	CL1
Slip resistance (ramp)	R-9
Slip resistance (bare feet)	A
4s	Wet - 33 / Dry - 59

\*ISO-13006:2018 UNE-EN 14411:2016

### System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## PACKING

Sales units per box	1.874977 M2/BOX
Sales units per pallet	44.999438 M2/PAL
Sales units per unit	0.374995 M2/PIECE

## System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.