

**Model:** AGED DARK NAT.PV6 120X120(A)

**Codes:** 100331035

**Absorption:** Bla - Porcelanico (E<=0.1%)



## DIMENSIONAL FEATURES UNE-EN ISO 10545-2

Length	1200 MM	
Thickness	6 MM	
Width	1200 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

\*ISO-13006:2015 UNE-EN 14411:2017

## MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11

Breaking strength	1118.5 N
Modulus of rupture	43.6 N/MM2
Crack resistance	RESISTE 3 CICLOS

\*ISO-13006:2015 UNE-EN 14411:2017

## HYGIENIC FEATURES UNE-EN ISO 10545-13-14

Chemical resistance	MÍNIMO CLASE B
Stain resistance	CLASE 5
Resistance to thermal shock	RESISTE

\*ISO-13006:2015 UNE-EN 14411:2017

## ANTI-SLIP VALUE CEN/TS 41901/02, DIN-51130 y ASTM A137.1

Slip resistance (pendulum-wet)	CL1
Slip resistance (pendulum-dry)	>40*

\*ISO-13006:2015 UNE-EN 14411:2017

## SCOPE OF USE

Technical code-1	Use on medium traffic floors
Technical code-2	Dry interior floors

### System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## PACKING

Sales units per box	2.880184 M2/BOX
Sales units per pallet	80.645161 M2/PAL
Sales units per unit	1.440092 M2/PIECE

## System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.